



# PERFORMANCE GUIDE

[www.MACTac.com](http://www.MACTac.com)

Version #2 (0811)

Approved by J. S.

## **PRODUCT: IMAGin<sup>®</sup> B-free<sup>®</sup> Gruv<sup>™</sup> GV429R**

**PRODUCT DESCRIPTION:** GV429R is a 3.0-mil **gloss** white, soft calendered PVC film designed for solvent and UV inkjet printing. The product is coated on one side with a removable, opaque, acrylic pressure sensitive adhesive with air egress technology and supplied with a 98# polycoated liner.

GV429R is designed for indoor or outdoor medium-term advertising and promotion applications on flat or simple curved surfaces. Use of PERMACOLOR<sup>®</sup> ColorGard<sup>™</sup> or RAYZor<sup>™</sup> overlaminating films will extend the life of the graphic.

| <b>PHYSICAL PROPERTIES:</b>  | <b>TYPICAL VALUES*</b>     | <b>TEST METHOD</b>                 |
|--|----------------------------|------------------------------------|
| <b>Peel Adhesion, lb. /in. (N/25mm)</b>  |                            |                                    |
| 180° on glass, - 24 hr..   | 1.6 (7)                    | FTM-1                              |
| 180° on SS, - 24 hr..  | 1.2 (5.5)                  | PSTC-1                             |
| <b>Quick Tack on Glass, lb. /in<sup>2</sup> (N/25mm)</b>                             | 1.0 (4.4)                  | FTM-9                              |
| <b>Quick Tack on SS,</b>   | 0.9 (3.8)                  | MACTac CTM-25                      |
| <b>Dimensional Stability, (%)</b>  |                            |                                    |
| 48 hours @ 158°F   | max 0.5                    | 5" x 5" Sample bonded to aluminum. |
| <b>Surface Burning Characteristics</b>   |                            |                                    |
| Flame Spread   | 0                          | ASTM E84-01 or ANSI/NFPA 255 or    |
| Smoke Density  | 65                         | UCB 8-1                            |
| This product meets: ANSI - Class A, NFPA - Class A and UCB - Class 1 specifications. |                            |                                    |
| <b>Temperature Ranges,</b>   |                            |                                    |
| Minimum Application:   | 50°F (+10°C)               |                                    |
| End Use:   | -40 to 158°F (-40 to 70°C) |                                    |

**INTENDED FOR:** Wide format, eco-solvent, solvent-based and UV-cured inkjet and screen printing. To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used. Profiles can be obtained from our Distributors or can be downloaded from [www.mactac.com/graphics](http://www.mactac.com/graphics). Printer and heater settings and ICC profiles can also be downloaded from some O.E.M. or software manufacturer's websites.

GV429R is also a great for bubble-free applications of indoor wall murals.

**NOT INTENDED FOR:** Partial Vehicle wraps or complex surfaces.

The ICC profiles are provided solely as a customer resource. Print environments, the individual nature of printing systems, inks and software can significantly affect output. It is the customer's responsibility to determine the suitability of any profile for use in their specific print environment.

**DURABILITY:** The outdoor durability of the unprinted film is 4 years. Overlamination of the inkjet-printed material with PERMACOLOR ColorGard or RAYZor overlaminating films delays color fading that may occur over time. Color fading is mainly dependent upon the inks quality (see technical data sheets given by the ink manufacturers) and pressure sensitive media being used.

**REMOVABILITY:** GV429R is cleanly removable from most sound surfaces for up to one year. Some substrates are affected by the application of the GV429R such as acrylic glass, polycarbonate, polystyrene, nitro-cellulose paints and plasticized PVC. Besides damaging the substrate, removal could be difficult

**LIMITATIONS:** Due to the wide variability of interior walls, sealants and paints, no claims for successful applications to or removal from painted wall surfaces are made by MACtac. It is the users' responsibility to determine the products suitability for the intended wall.

- 1) **The user is responsible for determining the product's suitability, including adhesion and if needed, removal characteristics when used in applications other than listed specifically in this Performance Guide.**
- 2) **If there are any questions about applications, please contact your MACtac sales representative to discuss your requirements for recommendations.**
- 3) **If this is a printed Performance Guide it is an uncontrolled document. Please check the MACtac website for the latest, most up-to-date version.**

**RECOMMENDATIONS:**

Always test your combination of B-free Gruv products, inks and laminating films prior to commercial use.

1. **Printing Conditions:** Print in conditioned pressroom at  $\pm 73^{\circ}\text{F}$  ( $23^{\circ}\text{C}$ ) and 50% RH. The maximum allowable ink saturation is 270%.
2. **Drying Step:** It is **critical** the GV429R print is properly dried prior to cutting, lamination or application. We strongly recommend leaving the print *open to the air* (not rolled up in a tube) for a minimum of 24 hours prior to lamination or application. Residual solvents in the vinyl and adhesive will negatively affect the bubble free properties of the adhesive and can cause a significant build, or loss, in adhesion resulting in potential substrate or graphic failure and/or more residual adhesive being left behind upon removal. Additional hot air drying or IR drying will speed up the drying process and shorten the overall drying time.
3. **Laminating Conditions:** Ensure print is perfectly dry. Material must have 24 - 48 hr. drying time *open to the air*, not rolled up in a tube, prior to lamination or transportation. If the printed graphic is likely to be exposed to corrosive liquids, smoke, fumes, and highly polluted areas or there is a likelihood of scratching, it is highly recommended to laminate with **PERMACOLOR ColorGard** series overlaminating films.
4. **Not recommended for surfaces including, but not limited to** rubber and plastic, aged paint (chalking) and metals (corrosion or oxidation), improperly cured paint, surfaces with poor paint-to-surface adhesion, over existing graphics that must remain upon removal, oily surfaces, unpainted wood, etc.
5. **Transportation Conditions:** To allow for easy transportation, B-free Gruv series can be rolled up, with the image out, with a minimum diameter of 6 inches (15cm). When the image is not protected by an overlamine, make sure the print is completely dry and protected in a plastic bag. During transportation or storage, avoid exposing them to extreme temperature and humidity changes.

**SHELF LIFE:**

2 year from Date of Manufacture when stored at 60 to 77°F (15/25°C) and 50% relative humidity in the original package.

*\* Values given are typical and are not necessarily for use in specification.*

**CALL 1-800-401-5005 for additional product information**

**IMPORTANT NOTICE:** The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

<sup>TM</sup> Trademark of Morgan Adhesives Company.  
© Registered Trademark of Morgan Adhesives Company.  
www.MACtac.com

